

POLYASPARTIC 7500

PRODUCT DESCRIPTION AND USE

Polyaspartic 7500 is a two component, high solids, aliphatic Polyaspartic. This unique new resin chemistry has provided the raw materials to formulate this coating that gives the desirable properties of polyester-polyurethane materials with shorter cure time and less film thickness limitations. Polyaspartic 7500 is a low viscosity, easy to handle product that gives very high gloss finishes that are both hard and abrasion resistant. This material releases soil easily and has excellent resistance to a broad range of chemicals. Unlike conventional polyurea materials, Polyaspartic 7500 has enough work time to be applied by brush and roller. It is very rapid curing and can be returned to full service in 24 hours. For exterior applications, a UV stabilizer package is incorporated to ensure long-term gloss retention and resistance to yellowing.

Polyaspartic 7500 was developed as a high performance coating for various protective coatings and seamless flooring applications. Polyaspartic 7500 is ideally suited for use as a finish coat in color chip and color quartz flooring, automotive repair facilities, aircraft hangars, clean rooms and various types of decorative architectural concrete applications.

Chemical Composition

Hydroxyl functional polyaspartic crosslinked with aliphatic isocyanate.

Colors

Available in clear only, product may be tinted with 7500 pigment packs

Limitations

- Do not allow to puddle. Film thickness must not exceed 10 mils.

TECHNICAL DATA

Physical Properties

Mixing Ratio, by Volume	1-1
Solids Content, by Weight	77%
Solids Content, by Volume	75%
V.O.C.	400 gms/ltr.
Viscosity, cps (77 degrees)	200
Pot Life, (77 degrees, 25% R.H.).....	20 minutes

Pot Life is reduced by increasing humidity and/or temperature.

WARRANTY INFORMATION

Arizona Polymer Flooring guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. ARIZONA POLYMER FLOORING MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. Arizona Polymer Flooring shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. Arizona Polymer Flooring shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.

HIGH PERFORMANCE CONCRETE COATING SYSTEM

Physical Properties (Cont'd.)

Dry Times. (77 degrees, 25% R.H.)
Dry to Touch..... 1 hours
Light Traffic..... 4 hours
Vehicle Traffic..... 24 hours
Full Chemical Resistance..... 72 hours

Performance Properties

Gloss (60 degrees) 95
Hardness (Pendulum)..... 172
Adhesion to concrete (ASTM D-451)..... concrete fails before loss of bond
Tabor Abrasion (1000 gm. load 1,000 cycles, CS17 wheel)36 mg loss

CHEMICAL AND STAIN RESISTANCE (ASTM D-1308 24 HOUR IMMERSION)

Urine no effect
Blood..... no effect
Whiskey no effect
Black Ink no effect
Brake Fluid..... no effect
Gasoline..... no effect
Skydrol B-4 no effect
Hydraulic Fluid #83282..... no effect
Mineral Spirits no effect
Xylene no effect
MEKfilm softened
50% Sodium Hydroxide no effect
25% Hydrochloric Acid no effect
25% Sulphuric Acid no effect
25% Acetic Acid..... no effect
25% Nitric Acidfilm blistered

GENERAL INFORMATION

Moisture Vapor Emissions Precautions

All interior concrete floors not poured over an effective moisture vapor retarder are subject to possible moisture vapor transmission that may lead to blistering and failure of the coating system. It is the coating applicator’s responsibility to conduct calcium chloride and relative humidity probe testing to determine if excessive levels of vapor emissions are present before applying any coatings. APF can supply moisture remediation products. Consult our technical service department. Arizona Polymer Flooring and its sales agents will not be responsible for coating failures due to undetected moisture vapor emissions.

Surface Preparation

Concrete must be cured 30 days and be clean, structurally sound, and free of wax, loose paint or curing compounds. Concrete should be shotblasted, or diamond ground to achieve a minimum 5 mil profile. If more than 12 hours has elapsed between coats or the coating cannot be indented with a fingernail, abrade surface with 80-100 grit sandpaper or screen to ensure intercoat adhesion.

Mixing Instructions

The mixing ratio is 1 Parts A to 1Parts B by volume. **Mix for 1 full minute using a slow speed drill, scraping the bottom and sides of the mixing container.** Mix only that amount which can be applied within 20 minutes. Additional solvent may be added up to 10% to further lower the application viscosity and extend the work time. Acetone is the recommended solvent.

Application Recommendations

Polyaspartic 7500 is a very reactive material and requires special application techniques. It may be brushed, rolled or sprayed using plural component spray equipment. Easy application is accomplished by pouring the freshly mixed product on the floor, spreading to the desired thickness with a rubber squeegee, and finish rolling immediately with a 18 inch roller. The mechanic rolling the material should wear spiked shoes to walk on the wet material. Because the material sets quickly, change roller covers every hour.

Application of the material must be done immediately after mixing. On large jobs, be sure to have enough mechanics to keep a wet edge. Application rate should be kept above 160 sq. ft. per gallon (10 mils). **Thicker films may entrap solvent or cause CO₂ bubbles. If allowed to puddle, CO₂ bubbles will appear as frosted areas.**

Handling Precautions

Use only with adequate ventilation/or a cartridge type respirator designed to be used for isocyanates. Avoid contact with skin, wear protective gloves. **Read Material Safety Data Sheet before using.**

Slip and Fall Precautions

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip-resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. Arizona Polymer Flooring recommends the use of angular slip-resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. Arizona Polymer Flooring or its sales agents will not be responsible for injury incurred in a slip and fall accident.