

SYSTEM DATASHEET: COLORCHROME SYSTEM

SYSTEM DESCRIPTION

The ColorChrome System is a metallic, seamless resinous flooring system. The designer flooring system possesses a truly unique, three-dimensional appearance that can vary from soft and subtle to striking and vivid. The use of high-performance resins make ColorChrome an exceptionally durable and long-lasting flooring system.

PRODUCT USES

ColorChrome is designed for any commercial or residential application where a durable and elegant floor is desired. This includes dining areas, restrooms, bars and night clubs, commercial interiors, sporting venues, residential interiors and garage floors.

FEATURES & BENEFITS

- Seamless Surface
- Abrasion Resistant
- Chemical Resistant
- Easily Cleaned
- Excellent Aesthetics

LIMITATIONS

Not suitable for exterior applications.

COLORS

ColorChrome is available in 20 standard colors. Please refer to our Standard Color Chart.

SURFACE PREPARATION

Concrete surface must be cleaned and profiled. Refer to the detailed ColorChrome installation instructions for more information.

PRODUCTS

Pigment: ColorChrome Pigment

Primers: Epoxy 100, Epoxy 200

Base resin: Epoxy 400, Epoxy 400 UVR

Top coat: Polyurethane 100, Polyurethane 100 VOC,

Polyurethane 501, Polyurea 5000

PHYSICAL PROPERTIES

| | |
|--|------------------------------------|
| Tensile Strength (ASTM D 638): | 6,230 psi |
| Ultimate Elongation % (ASTM D 638): | 11 |
| Compressive Yield Strength (ASTM D 695): | 9,850 psi. |
| Ultimate Compressive Strength (ASTM D 695): | 19,501 psi. |
| Ultimate Flexural Strength (ASTM D 790): | 9,680 psi. |
| Hardness, Shore D (ASTM D 2240): | 83 |
| Abrasion Resistance (ASTM D 4060): | 34 mg loss |
| Bond Strength to Concrete (ACI 503.4-2.3.2.2): | Concrete fails before loss of bond |

CHEMICAL RESISTANCE

Refer to Arizona Polymer Flooring Chemical Resistance Guide for full system chemical resistance.

CONCRETE MOISTURE

Calcium chloride in accordance with ASTM-F1869 or relative humidity probe testing in accordance with ASTM-F2170. In the event that test results in 3 pounds per 1000 sq. ft. per 24 hours, or 75% relative humidity, please refer to Arizona Polymer Flooring VaporSolve product information or go to www.vaporsolve.com.

INSTALLATION

Please refer to ColorChrome System installation guidelines for information and instructions.

SLIP & FALL PRECAUTIONS

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip-resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. Arizona Polymer Flooring recommends the use of angular slip-resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. Arizona Polymer Flooring or its sales agents will not be responsible for injury incurred in a slip and fall accident.