

# OIL STOP PRIMER

#### PRODUCT DESCRIPTION

APF Oil Stop Primer is a low viscosity, 100% solids resin designed for use as a primer on concrete slabs that are contaminated with hydrocarbons, such as motor oil, solvents, cutting oils and hydraulics fluids but are otherwise sound. It possesses outstanding adhesion and surface tolerance making it ideal for challenging applications such as these.

APF Oil Stop Primer is not recommended for food, beverage, harsh chemical, or routine hot water wash-down applications. Consult APF Technical Service for more information.

# **USES**

- Garages
- Machine Shops
- Warehouse

#### **ADVANTAGES**

Allows application of finish coats to concrete that is moderately contaminated with imbedded hydrocarbon based oils

#### **COLORS**

Clear, do not add pigment.

#### **PACKAGING**

Supplied in complete A+B 1.25 gallon (4.73 L), 25 gallon (94.6 L). Mix ratio 3A: 2B

### SURFACE PREPARATION

Concrete must be cured for at least 30 days and be clean, structurally sound, and free of wax, loose paint or curing compounds. Concrete should be shot blasted to achieve a surface minimum texture of ICRI 3 - 4. Refer to ICRI Technical Guidelines 310-330 Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, Polymer Overlays, and Concrete Repair. Acid etching is not recommended and will void Manufacturer's warranty. Carefully follow the guidelines listed in the Arizona Polymer Flooring published application instructions available at <a href="https://www.apfepoxy.com">www.apfepoxy.com</a>. Vacuum prepared concrete surface to remove all dust. Previously coated surfaces that are soundly adhered must be mechanically cleaned and abraded to achieve uniformly gloss-free, open texture.

Mixing Ratio by Volume  VOC  1 g/l Solids Content, by Volume 100% Tensile Strength (ASTM D-638) Ultimate Elongation, (ASTM D-638) 11% Compressive Yield Strength, (ASTM D-695) Flexural Strength, psi (ASTM D-790) 9,680 psi Cure Time (77°F) Dry to Touch Recoat Final Flooring Application 18 Hours	TECHNICAL DATA	
Solids Content, by Volume  Tensile Strength (ASTM D-638)  Ultimate Elongation, (ASTM D-638)  Compressive Yield Strength, (ASTM D-695)  Flexural Strength, psi (ASTM D-790)  Cure Time (77°F)  Dry to Touch  78 Hours	Mixing Ratio by Volume	3A:2B
Tensile Strength (ASTM D-638) 6,230  Ultimate Elongation, (ASTM D-638) 11%  Compressive Yield Strength, (ASTM D-695) 9,850 psi  Flexural Strength, psi (ASTM D-790) 9,680 psi  Cure Time (77°F)  Dry to Touch ~8 Hours	VOC	<1 g/l
Ultimate Elongation, (ASTM D-638)  Compressive Yield Strength, (ASTM D-695)  Flexural Strength, psi (ASTM D-790)  9,680 psi  Cure Time (77°F)  Dry to Touch ~8 Hours	Solids Content, by Volume	100%
Compressive Yield Strength, (ASTM D-695) 9,850 psi Flexural Strength, psi (ASTM D-790) 9,680 psi Cure Time (77°F)  Dry to Touch ~8 Hours	Tensile Strength (ASTM D-638)	6,230
Flexural Strength, psi (ASTM D-790) 9,680 psi  Cure Time (77°F)  Dry to Touch ~8 Hours	Ultimate Elongation, (ASTM D-638)	11%
Cure Time (77°F)  Dry to Touch ~8 Hours	Compressive Yield Strength, (ASTM D-695)	9,850 psi
Dry to Touch ~8 Hours	Flexural Strength, psi (ASTM D-790)	9,680 psi
2.7 10 100011	Cure Time (77°F)	
Recoat Final Flooring Application <18 Hours	Dry to Touch	~8 Hours
9 PF	Recoat Final Flooring Application	<18 Hours
Full Cure ~7 Days	Full Cure	~7 Days

Higher temperatures reduce pot life and cure time, lower temperatures increase pot life and cure time.

#### **MIXING**

APF Oil Stop Primer is packaged in premeasured and bulk units. Proper proportioning and homogenization are critical for success. Mixing ratio is 3A: 2B. Premix both components for 3 minutes prior to blending. Drum units should be mechanically premixed with electric or pneumatic drum head mixer. Do not attempt to hand mix. Be sure to move the drill around the mixing container scraping the sidewalls and bottom.

Add component B to component A and mix with medium speed drill mixer for three [3] minutes.

#### **APPLICATION**

Apply with squeegee, back roll with quality 1/4- or 3/8-inch solvent resistant roller cover. Apply in thin layer of 12 - 16 mils. Do not apply by dip-and-roll, distribute material on concrete surface immediately after mixing. Ensure that primed surface is pore and pin-hole free. Apply second coat if necessary to ensure pore-free surface for subsequent applications.



# OIL STOP PRIMER

#### **CONCRETE MOISTURE**

Test for concrete moisture in accordance with ASTM F2170 – 19. If moisture is indicated to be in excess of 85%, do not apply. Consult APF Technical Service for further information.

# **LIMITATIONS**

- Concrete must be free of liquid hydrocarbon contamination.
- A test patch should always be performed to verify adhesion.
- Do not apply in temperatures below 50 F.
- Coating will yellow when exposed to UV light

#### **SHELF LIFE**

One [1] year from date of manufacture, in original unopened container. Store away from heat sources between  $50^{\circ}F$  and  $85^{\circ}F$  ( $10^{\circ}C - 30^{\circ}C$ ).

#### **HANDLING & SAFETY**

Use only with adequate ventilation. Appropriate cartridge-type respirator must be used during application in confined areas. Avoid contact with skin; wear protective gloves and safety glasses. User must read and understand Safety Data Sheet before using. APF Safety Data Sheets are available at <a href="https://www.apfepoxy.">www.apfepoxy.</a>

APF Oil Stop Primer PDS 04.19.21

#### STANDARD WARRANTY STATEMENT

ICP BUILDING SOLUTIONS GROUP, the owner of Arizona Polymer Flooring, warrants that the product is produced within specifications and is free from defect. No warranty shall be in effect until ICP Building Solutions Group Terms and Conditions of Sales are met, including payment and cooperative promotional considerations. ICP Building Solutions Group warrants that the covered product is free of defect and suitable for the specified purpose for a period of one (1) year from the date of shipment, provided the product is installed within its published shelf life, in strict conformance with specifications, and/or written project-specific installation guidance from authorized representation. ICP Building Solutions Group warrants only when product is handled, stored, mixed and applied in accordance with published recommendations. It is purchaser responsibility to initiate any claim against this warranty within a reasonable time. If determined by ICP that the product does not meet this warranty, the liability of ICP Building Solutions Group shall be limited to refund of the purchase price or provision of replacement product, neither needing to exceed the affected area as determined by a person authorized to perform technical representation for ICP Building Solutions Group. To obtain a replacement or refund the customer must provide written notice containing full details of the non-conformity suspected. The purchaser, owner or their representative shall notify ICP Building Solutions Group in writing, within five (5) working days concerning any potential defect, or as needed before conditions deteriorate and increase repair costs. ICP Building Solutions Group reserves the right to inspect the non-conforming material prior to replacement. ICP Building Solutions Group may in its discretion refund the purchase price received by ICP Building Solutions Group in lieu of replacing the material. Except for the expressed warranty stated above, there are no other warranties, expressed or implied, including without limitation, any im

